X-ray and Neutron Microdiffraction

Gene E. Ice

Materials Science and Technology Division

Oak Ridge National Laboratory



2014 Neutron X-ray Summer School

Two words

Spatial Resolution

Materials characterization begins 3 questions

- What is the elemental composition?
- What is the crystal/local structure?
- What are the defects?





X-rays and neutrons probe structure and defects through scattering (diffraction)

Spatial resolution essential!



- **Most materials** ***polycrystalline*** **(0.1-50 μm)**
  - **Anisotropic**
  - **Heterogeneous**
  - **Plastic/elastic deformation/ diffusion/ oxidation/**

- **Even** ***within*** **single and "perfect" crystal:**
  - **Strain**
  - **Defects**
  - **Spontaneously organize to reduce energy**



Spatial resolution essential for most advanced energy systems

New X-ray/ Neutron Sources Changing the Possible

- **Brilliance figure-of-merit for spatially-resolved exp.**
- **X-ray brilliance doubling faster than Moore's law**
- **SNS with 10x brilliance 100x more efficient detectors**

TOPAZ/ SNS



Spatial Resolving Optics Improving Rapidly

- **X-ray focal spot size routinely below 100 nm**
- **Neutron focusing optics below 100 µm**



Neutron optics with <70 µm Focus



X-ray micro/nanofocusing optics rapidly evolving

- **CRL-50 nm**
- **FZP<30 nm**
- **Kinoform <70 nm**
- **MLL <15 nm**
- **KB <7 nm**
- **NMM<80 nm**



Diffraction mapping emerging area in electron and x-ray microscopy

- EBSD-transformed study of polycrystals
  - Surface phase
  - Surface orientation
  - FiB-3D mesoscale structure





- 4D X-ray microscopy Lienert et al.
  - Time resolved
  - Deep penetration



- Coherent X-ray Diffraction (Robinson et al.)
  - Simple structures



- Polychromatic X-ray microdiffraction
  - Phase/texture/***strain***/
  - ***Nondestructive***
  - ***Submicron***





_name

OAK RIDGE National Laboratory

X-ray Micro/nanoprobe beams map chemistry and structure



Monochromatic micro crystallography probes simple crystal systems



Wide-range of focusing choices



Ferroelectrics ideal samples



Thompson et al. study dimensionality of ferroelectricity

- Thickness
- Ribbons
- Dynamics



Diffraction from a ferroelectric stripe

Ferroelectricity found with few unit cells

Cai et al. and others study ultra-small nanocrystalline volumes with existing microbeams



•150 nm beam resolves crystalline substructure in individual Sn_2O_3 nanobelts

Fluorescence map

Diffraction map





APS *Nanoprobe* – opens new opportunities for spatially resolved

- **Diffraction proposals compelling**
- **Physics of small**
- **Integrated circuit materials**

~30 nm now

<10 nm possible in future

NSLSII ~1 nm!

4DXRD Microscope emerging tool for studying mesoscale dynamics-single rotations

- Singly focused monobeam illuminates numerous grains
  - Bragg condition satisfied by single rotation
  - *Time resolution! (4D)*



- Grain outline determined
  - Ray tracing
  - conical slit
  - Back-projection tomography



- E>50 keV allows deep measurements

Best with high-energy beams/Beamline 1 at APS

4DXRD Microscope powerful dynamics probe

- **Recrystallization growth individual grains-deep**
  - **E. M. Lauridsen, D. Juul Jensen, U. Lienert and H.F. Poulsen (2000). *Scripta Mater.,* *43, 561-566***
- **Rotations/texture evolution individual grains during deformation**
  - **Tests deformation models**
  - **L. Margulies, G. Winther and H.F. Poulsen, Science** 291, **2392-2394 (2001).**





4DXRD Microscope provides additional powerful capabilities

- **Grain boundary mapping in coarse grained materials-5μm**
  - **Poulsen et al. J. Appl. Cryst. 34 751-756 (2001)**



- **Single crystal refinement for polycrystals**
- **Macro/microstrain**



Strain tensor elements in torsion sample

Ideal for neutrons! But needs high-resolution detectors!

Polychromatic simplifies microdiffraction

Solves intrinsic problem with conventional microdiffraction-

-Sample does not need to be rotated!



Special software required- Can index polycrystalline samples

3D nondestructive probe of stress/strain/crystal structure!

3-D X-ray Crystal Microscope has specialized elements



<0.25 x 0.25 x 0.5 μm^3
strain~10^{-4}-10^{-5}





Provides Submicron 3D Maps With New Information

- **Phase boundaries**





- **Grain boundaries(3D)**






- **Elastic strain**

- **Deformation /Nye tensor**




Nondestructive!

Laue methods essential for some samples



Differential aperture microscopy resolves submicron along incident beam!

- Simplifies data interpretation
- Submicron Z resolution
- Isolates weak diffraction from strong
- First demonstration by Larson et al. on deformed Cu -





As wire moves its edge cuts through Laue spots

- **Near-surface fluorescence provides moving shadow**

- **Long scans needed for deep penetration**



Measurements of elastic strain tensor *inside* bent single crystal Si illustrate power of DAXM





Orientations to 0.001°

Larson et al. J. Eng. Mat. and Tech. 130 021024 (2008) ORR award

Maps crystal properties in 3D

- Phase
- Texture (orientation)
- Elastic strain tensor
- Nye tensor (deformation)





T. Bieler et al.

Experimental Hutch 34ID-E at UNICAT, Advance Photon Source



Ongoing research too extensive to cover

- **Fracture/stress localization in thin films**
- **Residual stresses/ deformation/ grain boundary network near welds**
- **Complex phase patterned materials**
- **Extreme environmental chambers**







OAK RIDGE National Laboratory

Ongoing too extensive continued..

- **Domain wall structure measurements**
- **Sn whisker growth**
- **High-performance alloys**
- **Nanomaterials**





Energy scans allow structure determination

- Generalization of orientation software can identify phases
- Energy scans provide integrated reflectivities.
- Identified two minor crystal phases tetragonal/ hexagonal

Cannot be found by powder



BAM braze $Pd_{40}Cu_{30}Ni_{10}P_{20}$



OAK RIDGE National Laboratory

Grain-growth/ Budai et al. characterized epitaxial growth RABiTS

Optical: ~50μm grains



CCD Laue Patterns





CeO_2 Observation:

Exact epitaxy for growth at low T; lattice tilts at high T

Relative CeO_2 orientation depends deposition temperature





Step edge growth- good:

Crystallographic tilt towards ⊥

Tilt increases monotonically with miscut

Island growth-bad:

In-situ observations of 3D Grain Growth





Hot-rolled (200°C 1xxx Al(~1%Fe,Si) Alcoa Polycrystal

Thermal Grain Growth in Hot-Rolled Aluminum

1 µm pixels,   Boundaries: 5° & 20°



- **GB motions include both high-angle and low-angle boundaries**
- **Complete and detailed 3D evolution needed for validation of theories.**

Thermal Grain-Growth And Microstructure Refinement in Polycrystalline Al



- **3D X-ray Microscopy Measurements of Dislocation Density Finds Microstructure Refinement to Be Important**

Deformation mediated by "dislocations"

- **Individual dislocations can be seen with TEM-but…**

X-ray people complain thin electron samples Fundamentally different

Neutron people complain thin X-ray samples Fundamentally different

What is "thin" and "bulk"?



Edge dislocation



Screw Dislocation

Local orientation and plastic/elastic deformation mapped in pendeoepitaxially grown GaN



- **Reduced dislocations**
- **Direct confirmation of tilted wing structures**
- **New information on local plastic/elastic strain**



Deformation typically larger near surfaces/ grain boundaries



Deformation in polycrystals illustrates grain boundary behavior





Deformation induced rotations across grain boundaries sensitive to boundary type



Submicron spatially-resolved crystallography opens new opportunities



Do neural networks provide a path forward?

- **Visualization of 3D tensor data unsolved problem**
- **Human mind well adapted to 3D visualization based on binocular 3D data.**
- **Neural network not “limited” by streamlined processing of human brain**





Coherent diffraction offers promise for atomic resolution with focused beams

- **Focusing**
  - Better spatial resolution
  - Poorer field-of-view

- **2 nm with 3rd generation source and 1 μm focal spot**

- **2 Å with 10 nm spot- or 4th generation source**



Neutron microdiffraction additional opportunities



Magnetism

Atomic motions

Low Z materials



Nobel prize to Shull and Brockhouse

Focused beams extend neutron science

- Inhomogeneous samples
- Small samples in environmental chambers
- Spatial resolved distributions deep in samples





Even the most intense neutron source must be used efficiently

Neutron sources 10^{12} lower brilliance than advanced x-ray

Neutrons expensive 10^{13} more expensive!

10^{-16}\$ /x-ray

10^{-3}\$ /neutron

Increase divergence/ bandpass

10^{-9}\$/ neutron

Neutron microfocusing optics evolving

- Sagittal focusing optics < 300 μm
- Lobster eye optics ?
- NMM <100 μm
- Wolter optics<200 μm









"Deflected" KB™ can collect larger divergence

- **Basic element elliptical mirror**
- **Increase divergence with multiple reflections**
- **Optics within state-of-art**





2D Focusing complicated but possible

Gravity complicates polychromatic neutron microbeams

$$\Delta y_{total} \sim \frac{gF_1^2}{2v^2} M(1-M)$$

Tricks to reduce dispersion

- M~1
- M small
- F_1 small
- Reflections

$$m = \frac{1-\sqrt{2}}{\sqrt{2}}$$



Spallation neutron science intrinsically polychromatic

- **Analogous to polychromatic X-ray microdiffraction-*but includes* energy**
- **Allows for structure determination**
- **Absolute strain measurements**



SNAP experiments diffraction high pressure cells

- **Focusing optics work near theoretical limit**
- **Minor improvements should enable 25 micron measurements**





Neutron mirrors produce microbeams

- **Better signal-to-noise**
- **Resolve inhomogeneities**
- **Map crystal distributions**







Useable 25 μm beams?

Conclusion: Microdiffraction

- Addresses long-standing issues materials physics
- Techniques and instrumentation rapidly evolving
- Answers specific questions about materials systems (Energy materials)
- Extend x-ray and neutron characterization to new classes of samples.
  - Dangerous
  - Inhomogeneous
  - Samples in extreme environments



Materials structure tiny- intrinsically 3D
And spatial resolution- is needed urgently
The frontiers moving quickly now-excitements in the air
Though ask the average person- they really couldn't care

CHORUS

Nondispersive - optics change what we can see
Mesostructure- resolved by crystallography
Atomic defects quantified - so that we can surmise
Emergent structures origins- at the mesoscopic size

New optics and new methods- extend what we can do
With spatial resolution- time resolution too
Nondestructive lets us watch- materials deep inside
Chambers or complex system - where once they could hide

Emerging applications- I've tried to show a few
Energy materials- have challenges quite new
With x-ray and neutron beams- we now are freed
To study these materials- on the scale that we need